




INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ



PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated

19 August 2004

BEST AVAILABLE COPY

- 8 APR 2003

The Patent Office

GBAPR03 E798477-1 D01038
P01/7760 0.00-0308028.0

THE PATENT OFFICE

G

- 8 APR 2003

NEWPORT

The Patent Office
Cardiff Road
Newport
South Wales
NP10 8QQ

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference P303713GB

2. Patent application number
(The Patent Office will fill in this part)

0308028.0

3. Full name, address and postcode of the or of each applicant (underline all surnames)

University of Warwick
Gibbet Hill Road
Coventry
CV4 7AL
United Kingdom

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

UK. 7/8/02 4019162002

4. Title of the invention

Directional Impact Failure Material

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

WITHERS & ROGERS
Goldings House
2 Hays Lane
London
SE1 2HW

Patents ADP number (if you know it)

1776001 ✓

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

YES

9. Enter the number of sheets for any of the following items you are filing with this form.
Do not count copies of the same document

Continuation sheets of this form

Description 8

Claim(s) 2

Abstract 1

Drawing (s) 2 + 2 *He*

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature *Keith Tart*

Date 4.4.03

12. Name and daytime telephone number of person to contact in the United Kingdom Keith Tart 0121 245 3900

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least six weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500 505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Laminate Material

This invention relates to a laminate material made from thermoplastic polymers the impact strength of which depends upon the direction of impact; and to a method of making such a material.

Thermoplastic polymer materials are widely used in manufactured goods. Some such materials ; such as polycarbonates are very tough and are used extensively in the manufacturing industries. For example; polycarbonates are used for glazing applications where they have been found to provide excellent intruder resistance. However, in such applications the use of such a tough material hinders escape in an emergency; for example, from a crashed vehicle. There is therefore a need for materials that exhibit directional impact properties; that is varying strength on each face; for example, in sheet form such a material may be broken more easily by impacting the inner face than by impacting the outer face. Thus, vehicle glazing made of such a material could be relatively easy to break from the inside while retaining its normal strength in respect to outside impacts.

It is an object of this invention to provide a laminate thermoplastic polymer material with directional impact properties. It is a further object to provide a method for manufacturing such a material where the degree of weakness on a selected face can be controlled by appropriate selection of manufacturing process conditions.

In one aspect the invention is a laminate material comprising two components, a first thermoplastic polymer substrate and a second thermoplastic polymer film; wherein the film and substrate are directly bonded one to another and where substantially one face or side only of the substrate is laminated with film; and the film has many small flaws generated as a result of the manufacturing process such that in use the resistance of the substrate to a localised impact on a non-laminated face is significantly reduced by the presence of the flaws in the film layer.

In another aspect the invention is a laminate material comprising two components, a first thermoplastic polymer substrate and a second thermoplastic polymer blown film; wherein the

film and substrate are directly bonded one to another and where substantially one face or side of the substrate only is laminated with film; such that in use the resistance of the substrate to a localised impact on a non-laminated face is significantly reduced by the presence of the film layer. Preferably the polymer blown film is impact modified.

In a further aspect the invention comprises a method of making the above laminate material where thermal bonding is used to directly bond a first thermoplastic polymer substrate and a second thermoplastic impact modified polymer blown film. Preferably, the directional impact properties of the material are controlled by adjusting the strength of the thermal bonding. The temperature and/or pressure applied to bond the film and substrate may be varied in order to adjust the strength of the thermal bonding. Preferably, the thermoplastic polymer substrate is a polycarbonate material and the thermoplastic impact modified polymer blown film is a highly rubberised blown acrylic film. The thickness of the blown film may be between 50 and 250 μm and is preferably about 100 μm .

Typically, the material may be manufactured in sheet form. However, the invention may also be used where the material is shaped and has varying thickness; for example a vehicle windscreen. The material of the invention may optionally have added weathering materials or colouring agents.

The material of the invention has many advantageous safety applications; for example, glazing windows and partitions in vehicles and also domestic/commercial applications such as glazing in windows or showers enclosures in the home; where escape in an emergency is an important issue.

The invention will now be described by reference to the following figures;

Figure 1 shows schematically the main features of known apparatus used for manufacturing blown film;

Figures 2a and 2b show schematically a laminated sheet according to the invention before and during a localised impact; and

Figure 3 is a bar chart that shows the impact resistance of unlaminated polycarbonate sheet material, and laminated polycarbonate sheet material (from both sides) prepared according to the method of the invention described in Example 1.

In order to achieve the desired directional impact properties it has been found that it is much preferred to use a blown film/layer. However, a layer produced by other means such as simple extrusion may also be used provided that many small surface flaws are present. Preferably, blown film is impact modified; that is it has been toughened, typically by adding rubberising agents. In the film blowing process (see Figure 1) plastic melt passes through an extruder (E) and a die (T) - that forms it into an annular shape, usually directed upwardly. A molten plastic tube emerges from the die and this is subjected to both a moderate internal air pressure generated by process air introduced via an air inlet (A), and a longitudinal force via take-off rolls (R'). The tube is cooled by air from an external air ring (R). Under these conditions the molten tube gradually expands into a larger diameter stable solid cylindrical "bubble" beyond the 'freeze' line (F). The bubble is gradually flattened in a collapsing device (C), which consists of a pair of converging, ladder-like sets of idler rolls, and thereafter by the take-off rolls (R') where it is handled as a thin flat film.

It has been found that blown film has many small flaws in its surface. These flaws play a vital role in achieving the object of the invention. When the non-laminated side of a material laminated according to the invention suffers a localised impact of sufficient intensity the surface of the film is put into tension (see Figures 2a and 2b) upon impact and flaws present in surface of the blown film, especially in the locality of the impact, will open to form a crack. A crack may be initiated at a very low energy level and the crack will then propagate backwardly first through the film and then to through the directly bonded substrate, with relative ease.

In simple terms, the blown film 'tears' easily in tension and the crack then propagates rapidly through the sample, causing brittle failure. This effect is most pronounced for localised impacts (as produced by sharp objects). If the impact is from a blunt object it will normally be spread over a larger area, and failure will not occur so readily. This property is particularly advantageous for glazing applications, where a single blow by a key/stiletto heel/hammer is

likely to induce failure, but a blow from an elbow or head would not. Thus, safety would not be compromised during an accident, but escape would be assisted after an accident.

It has been found most advantageous to employ an impact modified material for the blown film; typically a highly rubberised acrylic blown film. During a low energy level impact on the film face, the surface of the highly rubberised film is put into a compressive state by the impacting object and any flaws are effectively closed. A crack in the blown film is not initiated until a medium-to-high energy level is reached due to the cushioning effect of the compressed rubber molecules. The use of an impact modified blown film material, rather than simply a blown film material, advantageously results in the impact strength of the film face up side of the material being only marginally less than substrate alone (un-laminated material).

For a crack to progress through a medium it has to have sufficient energy at the crack tip to propagate. There must also be a continuing medium for the crack to travel through, i.e. good adhesion at the interface. If there is not good adhesion at the interface then delamination may occur; the crack tip is blunted and cannot continue through the sample. This phenomenon is known as 'film-debonding' and is caused by low interface toughness compared to that of the film and the substrate.

The following Examples detail methods for producing a sheet of material according to the invention. While in Examples 1 and 2 injection moulding was used to thermally bond the substrate and the blown film it has been found that other laminating process can be used such as co-extrusion, calendering etc..

Example 1

Seven samples were manufactured using conventional injection moulding. A 'blown' impact modified rubberised acrylic film was laid in a mould cavity, comprising a simple flat plaque, measuring 150 mm x 150 mm x 3 mm, with a conventional runner and gate system. The film used was 100 μ m thickness and was supplied by Polymer Extruded Products, 297 Ferry Street, Newark, New Jersey 07105.

Molten Polycarbonate was back-injected onto the film. The polycarbonate grade was Bayer Makrolon AL2647 (supplied by Bayer GmbH, Germany). The process settings (see Table 1) were such that full mould fill and packing were obtained.

Finally, the samples were removed from the machine, the sprue and gates removed and then impact tested.

Table 1 - Process Data

Barrel Temperatures: 260° C to 280° C

Injection Temperature: 280 °C

Tool Temperature: 30 °C

Metering: - 92mm

Screw Speed: - 100rpm

Back Pressure: - 5 bar

Injection Speed: - 35 mm/s

Injection Pressure: - 175 bar

Changeover: - 5mm

Holding Time: - 15s

Holding Pressure: - 30 bar

Testing of Samples produced by Example 1

The samples produced via the method above were impact tested in two ways, the first with the film face up (i.e. film on the impact side) and secondly with the film face down (i.e. film opposite the impact face).

The impact tests used a Pneumatic Dart Impact machine equipped that complies with ASTM D3763-99 and a 12.5 mm radius hemispherical impact dart was used. The flat samples were placed in the clamp zone of the Dart Impact machine. When the safety door shuts the test pieces are hydraulically clamped in position. When the test is initiated the dart is fired downwards through the sample. The trials were conducted in accordance with ASTM D3763-99.

Three sets of samples were tested (see Table 1). Samples 1 to 7 relate to polycarbonate with no blown film laminate; Samples 8 to 14 relate to samples laminated according to the invention impacted upon the film face; and Samples 15 to 21 refers to samples laminated

according to the invention an impact tested on the non-film face. The samples were impacted using an initial dart height of 40 mm and an impact velocity of 4 ms^{-1} . A computer logged data for post-test analysis. For these data the total energy absorbed by the component before failure along with observations of the manner of failure, i.e. brittle or ductile was logged. Impact tests were also conducted with un laminated polycarbonate in order to provide a reference. The results are illustrated in Figure 3.

It can be seen that the blown film face up samples exhibited impact failure energy levels (58 Joules to 73 Joules) only slightly less than for un-laminated polycarbonate samples (73 Joules to 87 Joules) of similar dimension; both failing in a ductile manner. However, a significantly lower energy of 1.7 Joules to 6.1 Joules was required when the sample was impacted on the polycarbonate face side (film face down) and the samples failed in a brittle manner.

Similar experiments have also been undertaken with another commercial grade acrylic; Orogas DRT TM (available from Atofina - UK Head Office, Globe House, Bayley Street, Stalybridge, Cheshire SK15 1PY, United Kingdom)

It is believed that when a sample is impacted upon the film face, the film is placed into compression and any flaws effectively close and so do not initiate cracks and so the toughness and ductility of the polycarbonate is maintained.

Table 1 - Impact Strength Test Data

Sample Number	Impacted Upon	Peak Load (N)	Failure Mechanism	Total Energy Absorbed (J)
1	No Film	6519	Ductile	72.91
2	No Film	6860	Ductile	80.90
3	No Film	6875	Ductile	79.96
4	No Film	6947	Ductile	80.80
5	No Film	6926	Ductile	78.88
6	No Film	6675	Ductile	84.41
7	No Film	6800	Ductile	86.71
8	Film Face	6436	Ductile	63.57
9	Film Face	6403	Ductile	63.81
10	Film Face	6155	Ductile	57.89
11	Film Face	5616	Ductile	64.33
12	Film Face	6493	Ductile	72.50
13	Film Face	6070	Ductile	61.23
14	Film Face	6319	Ductile	67.66
15	Non Film Face	1048	Brittle	2.17
16	Non Film Face	663	Brittle	1.68
17	Non Film Face	1163	Brittle	4.89
18	Non Film Face	688	Brittle	1.78
19	Non Film Face	1433	Brittle	6.08
20	Non Film Face	998	Brittle	5.01
21	Non Film Face	904	Brittle	3.71

Example 2

By lowering the processing temperature of the polycarbonate material used for the substrate from 280° C to 260° C was found that it was possible to produce some samples that exhibited higher non film side impact strength than those discussed above, but still significantly lower than unlaminated polycarbonate components (see Table 2).

Closer inspection of the test pieces after impact testing revealed different failure characteristics. Firstly when impacted on the polycarbonate side samples failed in a ductile manner, similar to when the samples of Example 1 were impacted on the film side, and in contrast to the dramatic brittle 'explosion' failure observed for polycarbonate side tests undertaken (Example 1). Secondly, film in the area of the impact was severely stressed and de-laminated from the PC substrate in small pieces.

Thus, the level of energy required to induce failure can be increased or decreased by controlling the level of adhesion (direct bonding) between the film and the substrate; effectively using the film-substrate interface as a crack inhibitor. High interfacial adhesion means that the crack is able to propagate easily across the interface ; while low interfacial adhesion means that the crack has difficulty in crossing the interface as the film debonds from the substrate.

The interfacial strength of the thermal bond between the substrate and the blown film may be controlled by varying other process conditions such as injection temp, injection speed, holding pressure etc.

Table 2

Sample Number	Impacted Upon	Peak Load (N)	Total Energy Absorbed (J)
1	Non-Film Face	5627	42.06
2	Non-Film Face	5709	43.17
3	Non-Film Face	5490	41.24
4	Non-Film Face	5567	41.78
5	Non-Film Face	5740	43.30
6	Non-Film Face	5612	41.98
7	Non-Film Face	5730	43.22

CLAIMS


1. A laminate material comprising two components, a first thermoplastic polymer substrate and a second thermoplastic polymer film; wherein the film and substrate are directly bonded one to another and where substantially one face or side only of the substrate is laminated with film; and the film has many small flaws generated as a result of the manufacturing process such that in use the resistance of the substrate to a localised impact on a non-laminated face is significantly reduced by the presence of the flaws in the film layer.
2. A laminate material comprising two components, a first thermoplastic polymer substrate and a second thermoplastic polymer blown film; wherein the film and substrate are directly bonded one to another and where substantially one face or side of the substrate only is laminated with film; such that in use the resistance of the substrate to a localised impact on a non-laminated face is significantly reduced by the presence of the film layer.
3. A laminate material according to Claim 2 wherein the polymer blown film is impact modified.
4. A method of making a material according to any of Claims 1 or 3 where thermal bonding is used to directly bond the film and substrate.
5. A method according to Claim 4 wherein the directional impact properties of the material are controlled by adjusting the strength of the thermal bonding.
6. A method according to Claim 5 where the temperature and/or pressure applied to bond the film and substrate are varied in order to adjust the strength of the thermal bonding.
7. A method according to any of Claims 4 to 6 wherein the thermoplastic polymer substrate is a polycarbonate material.
8. A method according to any of Claims 4 to 7 wherein the film is a blown acrylic film.

9. A method according to any of Claims 4 to 8 wherein the film is between 50 and 250 μm thickness.
10. A method according to any of Claims 4 to 8 wherein the film is between 75 and 125 μm thickness.
11. A material made according to the method of any of Claims 4 to 10.
12. A material according to Claim 1, 2, 3 or 11 where the material is in the form of a sheet.
13. A laminate material comprising two components, a first layer and a second thermoplastic polymer layer, bonded to one another; the second layer having a lower resistance to a localised impact than the first layer prior to bonding; but wherein an impact against the face of the first layer of the laminate enables breakage of the laminate material with a lower impact energy than that required to enable breakage of said first layer prior to bonding.

Laminate Material

A laminate material comprising two components, a first thermoplastic polymer substrate and a second thermoplastic polymer blown film; wherein the film and substrate are directly bonded one to another and where substantially one face or side of the substrate only is laminated with film; such that in use the resistance of the substrate to a localised impact on a non-laminated face is significantly reduced by the presence of the film layer.

(Figure 2)




- (E) Extruder
- (T) Molten Tube
- (B) Bubble
- (P) Product
- (R') Pinch/Take-off Rolls
- (C) Collapsing Device
- (F) Freeze Line
- (R) Cooling Air Ring
- (T) Tool (die)
- (A) Air Inlet

Figure 1

Fig 2a



Film flaw



Impact Dart

Fig 2b



Flaw is opened and crack tip is initiated

Impact Resistance





Figure 3 - Bar Chart showing Impact Resistance of Samples prepared according to the Invention compared with Un-laminated Substrate

PCT/GB2004/001560



This Page is inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLORED OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REPERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images problems checked, please do not report the problems to the IFW Image Problem Mailbox